

ASX Announcement

23 November 2020

Further High Grade Results from the Sailfish Prospect

Pantoro Limited (**ASX:PNR**) (**Pantoro**) is pleased to advise further high-grade results from a short four hole follow up drilling program on the Sailfish prospect on Lake Cowan at the Norseman Gold Project (PNR 50%). Three out of the four holes drilled returned significant intercepts including:

- 1.6 m @ 61.78 g/t Au from 98.5 m downhole inc. 0.33 m @ 234.14 g/t Au (including 0.4 m of core loss calculated at 0 g/t Au).
- 0.65 m @ 38.66 g/t Au from 88.9 m downhole.
- 0.8 m @ 9.88 g/t Au from 93.0 m downhole.

The follow-up program was undertaken after the first eight hole program returned high grade intercepts including:

- 8.1 m @ 67.29 g/t Au from 78.6 m downhole inc. 0.7 m @ 521 g/t and 0.25 m @ 252 g/t Au (including 3.6 m of core loss calculated at 0 g/t Au).
- 3.5 m @ 2.56 g/t Au from 64 m downhole inc. 0.3 m @ 26.2 g/t Au (including 1.6 m of core loss calculated at 0 g/t Au).
- 1.8 m @ 4.25 g/t Au inc 0.95 m @ 7.71 g/t Au from 171.45 m downhole.

Refer to ASX release on 21 July 2020 titled 'Very High Grade Mineralisation Encountered on Lake Cowan'.

Based on the current drilling, Sailfish reef appears to be a shallow SE dipping lode system with hanging wall and footwall ore zones oriented similarly to the high grade HV1 vein at the Harlequin mine to the South. The new results have provided sufficient additional data for Pantoro to undertake a more substantial program to further refine understanding of deposit geometry, structural and lithological controls. The expanded program is planned to commence during November 2020.



Visible gold in hole SFDD20_011.

Pantoro Limited
ABN 30 003 207 467

Commenting on the results Pantoro Managing Director Paul Cmrlec said:

"Lake Cowan has long been recognised as an area of excellent exploration potential with little work completed historically. Drilling at Sailfish by Pantoro is the first exploration undertaken on the lake since the early 1990's, and the success that we have seen in the first target area at Sailfish provides great encouragement for our ongoing programs.

In addition to ongoing drilling at Sailfish and other prospects planned for the coming year, Pantoro has recently reprocessed the substantial geophysical data set at Norseman and has committed to additional gravity surveys to better define several additional targets ahead of drilling."

Sailfish Prospect

Mineralisation has been observed to be hosted in both the favourable Bluebird Gabbro (a megacrystic rock unit), hanging wall basalts and on the contact of the two units. The Bluebird Gabbro hosts the 1.8 MOz North Royal deposit, while some of the multiple lodes at Harlequin are hosted in the basalt units.




SFDD20_011: Bluebird Gabbro, Sailfish Reef, Footwall Basalt

Results from the twelve diamond holes drilled by Pantoro to date include:

- 1.6 m @ 61.78 g/t Au from 98.5 m downhole inc. 0.33 m @ 234.14 g/t Au (including 0.4 m of core loss calculated at 0g/t Au)
- 0.65 m @ 38.66 g/t Au from 88.9 m downhole.
- 0.8 m @ 9.88 g/t Au from 93.0 m downhole.
- 8.1 m @ 67.29 g/t Au from 78.6 m downhole inc. 0.7 m @ 521 g/t and 0.25 m @ 252 g/t Au (including 3.6 m of core loss calculated at 0g/t Au).
- 3.5 m @ 2.56 g/t Au from 64 m downhole inc. 0.3 m @ 26.2 g/t Au (including 1.6 m of core loss calculated at 0 g/t Au).

• 1.8 m @ 4.25 g/t Au inc 0.95 m @ 7.71 g/t Au from 171.45 m downhole.

Due to challenges in drilling below the lake cover affecting core recovery in the first round of drilling by Pantoro, the current follow up program was undertaken using larger (PQ) diameter core. The larger core resulted in substantially improved recovery within all rock units.



Sailfish Long Section: 385900E +/- 100m

Lake Cowan Exploration History

Historical operations at Norseman were primarily focussed on areas elevated above the local salt pans with Lake Cowan remaining devoid of exploration until 1989.

In 1990, a dedicated lake capable air core rig began testing on Lake Cowan beneath Tertiary sediment and Recent mud. This was the first successful drill rig of its type used on salt lakes in Australia with significant advances having been made since this time.

These initial programs were drilled on regional traverses at a spacing of 2 km by 400 m, with a small number of targets tested at a closer spacing. The more focussed programs were designed to test features defined by interpretation of magnetic data at the confluence of interpreted favourable stratigraphy and structure.

Sailfish was defined as part of this work along with the Harlequin and Cobbler deposits. After a short period of diamond drilling, the Harlequin deposit was discovered in 1991, causing exploration in other areas on the lake to be deferred. Harlequin was extensively drilled and mining commenced in 1995, producing early 800,000 ounces at approximately 10 g/t Au. As a result of changes in project ownership, other high priority targets sat dormant until Pantoro began work during 2020.

Ongoing Lake Work program

As part of the Lake work Pantoro is completing a review of the extensive geophysical datasets available to it from the CNGC database. This work is particularly focussed on the gravity and magnetic data in conjunction with the historic multi-element geochemical data. The company is planning to undertake a detailed gravity survey over the entire tenement package including the lakes early in 2021.

About the Norseman Gold Project (Pantoro 50%)

Pantoro Limited announced the major acquisition of 50% of the Norseman Gold Project in May 2019 and completion occurred on 9 July 2019. Pantoro is the manager of the unincorporated joint venture, and is responsible for defining and implementing work programs, and the day to day management of the operation.

The Norseman Gold Project is located in the Eastern Goldfields of Western Australia, at the southern end of the highly productive Norseman-Wiluna greenstone belt. The project lies approximately 725 km east of Perth, 200 km south of Kalgoorlie, and 200 km north of Esperance.

The current Mineral Resource is 4.2 million ounces of gold (100% basis). Many of the Mineral Resources defined to date remain open along strike and at depth, and many of the Mineral Resources have only been tested to shallow depths.

Pantoro recently completed its Phase One DFS for the project, defining an initial seven year life with average production of 108,000 ounces per annum once at steady state. For the purpose of the DFS, Pantoro has focused Mineral Resource and Ore Reserve definition drilling on six initial mining areas containing multiple deposits which are amenable to both open pit and underground mining. The DFS only considers 28% of the Resource at Norseman and large scale drill programs are ongoing.

The project comprises 146 near-contiguous mining tenements, most of which are pre-1994 Mining Leases. The tenure extends approximately 70 lineal kilometres of the highly prospective Norseman – Wiluna greenstone belt covering more than 1,000 square kilometres. Pantoro is focused on establishing a clear production development plan, and execution of that plan. The aim will be to initially establish an initial inventory of ~500,000 ounces to support a restart of operations.

Historically, the Norseman Gold Project areas have produced over 5.5 million ounces of gold since operations began in 1935, and is one of, if not the highest grade fields within the Yilgarn Craton. Pantoro is focused on establishing a clear production development plan, and has commenced drilling and other works required to convert Mineral Resources to Ore Reserves.

Enquiries

Paul Cmrlec | Managing Director | Ph: +61 8 6263 1110 | Email: admin@pantoro.com.au This announcement was authorised for release by Paul Cmrlec, Managing Director.

Appendix 1 – Table of Drill Results

Hole Number	Northing	Easting	RL	Dip (degrees)	Azimuth (degrees)	End of Hole Depth (m)		Downhole From (m)	Downhole To (m)	Downhole Intersection (m)	Au gpt (uncut)				
SFDD20 009	6449371	385933	263	-84	135	94		88.9	89.55	0.65	38.66				
3FDD20_009	0449371	363933	203	-84		94	incl.	88.9	89.15	0.25	48.15				
						120.4		75	75.5	0.5	1.06				
SFDD20_011	6449305	385892.136	263	-60	315		120.4	120.4	120.4	120.4	120.4	incl. 04m core loss	98.5	100.1	1.6
							incl.	99.55	99.88	0.33	234.14				
								73.5	74.5	1	1.32				
SFDD20_012	6449321	385876	263	-60	315	107.6		93	93.8	0.8	9.58				
							incl.	93	93.35	0.35	21				

Appendix 2 – JORC Code 2012 Edition – Table 1

SECTION 1: SAMPLING TECHNIQUES AND DATA

Criteria	JORC Code explanation	Commentary
Criteria Sampling techniques	 Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where 'industry standard' work has been done this would be relatively simple (eg 'reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay'). In other cases more 	 This release relates to results from a short 4 hole follow up program by Surface Diamond drill sampling of the Sailfish prospect located on Lake Cowan at the at the Norseman gold project. Diamond samples 2-5kg samples are dispatched to an external accredited laboratory (BVA Kalgoorlie and BVA Perth) where they are crushed and pulverized to a pulp (P90 75 micron) for fire assay (40g charge). All core is logged and sampled according to geology, with only selected samples assayed. Core is halved, with RHS of cutting line assayed, and the other half retained in core trays on site for further analysis. Samples are a maximum of 1.2m, with shorter intervals utilised according to geology to a minimum interval of15m where clearly defined mineralisation is evident.
	explanation may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.	 downhole core blocks . Visible gold is encountered and where observed during logging, Screen Fire Assays are also conducted Assays prior to June 1996 were sent to the WMC laboratory in Kalgoorlie. From July 1996 assays were sent to Analabs in Perth. Assaying procedures changed with the change in laboratory. Samples that were expected to assay well, were subjected to bulk pulverisation with duplicate assays at the WMC Laboratory and Screen Fire assaying at Analabs. The routine assaying method for other samples was aqua regia digest at WMC and fire assay at Analabs.
		 The bulk pulverisation routine used at the WMC Laboratory involved milling the entire sample to a nominal -75µm. Duplicate samples were split from the milled material and the sample was analysed using aqua regia digest and an atomic absorption finish. At Analabs the total sample was dried and milled in an LM5 mill to a nominal 90% passing -75µm. An analytical pulp of approximately 200g was sub sampled from the bulk and the milled residue was retained for future reference. All the preparation equipment was flushed with barren feldspar prior to the commencement of the job. A 50 gram sample was fused in a lead collection fire assay. The resultant prill is dissolved in aqua regia and the gold content of the sample is determined by AAS. For samples that contained visible free gold the screen fire assay method was used. It involved a 1000g sample screened through a 106µm mesh. The resulting plus and minus fractions were then analysed for gold by fire assay. Information reported included size fraction weight, coarse and fine fraction gold content and calculated gold

Criteria	ria JORC Code explanation		Cor	Commentary		
Drilling techniques	•	Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if	•	Surface DD – PQ diamond tails completed on rock roller pre-collars, All core has orientations completed where possible with confidence and quality marked accordingly.		
		so, by what method, etc).	•	Historic drilling was completed using surface drill rigs with standard core HQ and NQ.		
Drill sample recovery	•	Method of recording and assessing core and chip sample recoveries and results assessed. Measures taken to maximise sample recovery and ensure representative nature	•	All holes were logged at site by an experienced geologist or logging was supervised by an experienced geologist. Recovery and sample quality were visually observed and recorded.		
	•	of the samples.		DD – Minor core loss in this current program utilising PQ triple tube		
	•	Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.	•	Significant core loss has been noted in some prior holes drilled. This has occurred in transitional zones where HQ triple tube was utilized.		
Logging	•	Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.	•	Geological logging is completed or supervised by a qualified geologist and logging parameters include: depth from, depth to, condition, weathering, oxidation, lithology, texture, colour, alteration style, alteration intensity, alteration		
	•	Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.		mineralogy, sulphide content and composition, quartz content, veining, and general comments.		
		The total length and percentage of the relevant intersections logged.		100% of the holes are logged		
			•	Historic holes: CWS2, 4, 8, 9, 13, 16, 19, 22 & 30 were located and reviewed as part of the process.		
			•	Paper logs of historic drill holes have been cross checked to database as part of the validation.		

Criteria	JORC Code explanation	Commentary
Sub-sampling techniques and sample preparation	 If core, whether cut or sawn and whether quarter, half or all core taken. If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled 	• Core samples were sawn in half utilising an Almonte core-saw or with a block splitter in oxide and transitional material, with RHS of cutting line sent for assaying and the other half retained in core trays on site for future analysis.
	 For all sample types, the nature, quality and appropriateness of the sample preparation technique. 	For core samples, core was separated into sample intervals and separately bagged for analysis at the certified laboratory.
	• Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.	Core was cut under the supervision of an experienced geologist, it is routinely cut on the orientation line.
	 Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling. 	All mineralised zones are sampled as well as material considered barren either side of the mineralised interval
	Whether sample sizes are appropriate to the grain size of the material being	• Field duplicates i.e. other half of core or ¼ core has not been routinely sampled
	sampled.	Half core is considered appropriate for diamond drill samples.
		Historic Diamond Drilling
		Visual inspection of the of the referenced historic holes have been half cored and sampled either side of ore zones to define waste boundary.
		 Assays prior to June 1996 were sent to the WMC laboratory in Kalgoorlie. From July 1996 assays were sent to Analabs in Perth. Assaying procedures changed with the change in laboratory.
<u>(</u>)		Samples that were expected to assay well, were subjected to bulk pulverisation with duplicate assays at the WMC Laboratory and Screen Fire assaying at Analabs. The routine assaying method for other samples was aqua regia digest at WMC and fire assay at Analabs.
		• The bulk pulverisation routine used at the WMC Laboratory involved milling the entire sample to a nominal -75µm. Duplicate samples were split from the milled material and the sample was analysed using aqua regia digest and an atomic absorption finish.
		• At Analabs the total sample was dried and milled in an LM5 mill to a nominal 90% passing -75µm. An analytical pulp of approximately 200g was sub sampled from the bulk and the milled residue was retained for future reference. All the preparation equipment was flushed with barren feldspar prior to the commencement of the job. A 50 gram sample was fused in a lead collection fire assay. The resultant prill is dissolved in aqua regia and the gold content of the sample is determined by AAS. For samples that contained visible free gold the screen fire assay method was used. It involved a 1000g sample screened through a 106µm mesh. The resulting plus and minus fractions were then analysed for gold by fire assay. Information reported included size fraction weight, coarse and fine fraction gold content and calculated gold

Criteria	JORC Code explanation		Con	nmentary
Quality of assay data and laboratory tests	•	The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total. For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.	•	Assays are completed in a certified laboratory in Kalgoorlie WA and Perth WA. Gold assays are determined using fire assay with 40g charge. Where other elements are assayed using either AAS base metal suite or acid digest with ICP-MS finish. The methods used approach total mineral consumption and are typical of industry standard practice.
	•	Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.	•	No geophysical logging of drilling was performed. Lab standards, blanks and repeats are included as part of the QAQC system. In addition the laboratory has internal QAQC comprising standards, blanks and duplicates. Sample preparation checks of pulverising at the laboratory include tests to check that the standards of 90% passing 75 micron is being achieved. Follow-up re-assaying is performed by the laboratory upon company request following review of assay data. Acceptable bias and precision is noted in results given the nature of the deposit and the level of classification
Verification of sampling and assaying	•	The verification of significant intersections by either independent or alternative company personnel.	•	Significant intersections are noted in logging and checked with assay results by company personnel both on site and in Perth.
(15)	•	The use of twinned holes. Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.	•	SFDD20_005 is not a direct twin however it was drilled on a 315 degree azimuth (MGA94 Zone 52), proximal to historic hole CWS2 (refer to drill collar plan) and designed to intersect the interpreted vein system perpendicular to the strike.
		Discuss any adjustment to assay data.	•	All primary data is logged on paper and digitally and later entered into the SQL database. Data is visually checked for errors before being sent to company database manager for further validation and uploaded into an offsite database. Hard copies of original drill logs are kept in onsite office.
			•	Visual checks of the data re completed in Surpac mining software
			•	No adjustments have been made to assay data unless in instances where standard tolerances are not met and re-assay is ordered .
Location of data points	•	Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource	•	Diamond Drilling was downhole surveyed with a a Devi Gyro (Deviflex non-magnetic) survey tool with measurements taken every 3m.
		estimation. Specification of the grid system used.	•	Surface DD drilling is marked out using GPS and final pickups using DGPS collar pickups
	•	Quality and adequacy of topographic control.	•	The project lies in MGA 94, zone 51.
			•	Topographic control uses DGPS collar pickups and external survey RTK data and is considered adequate for use.
(1)			•	Pre Pantoro survey accuracy and quality assumed to industry standard
Data spacing and distribution		Data spacing for reporting of Exploration Results. Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied. Whether sample compositing has been applied.		Diamond drill spacing historically at Sailfish was been 50m spacing on drill lines with only 1-2 holes per line. This current round of drilling for 4 holes were located to test the stratigraphy and geological model, and were not on a set pattern. Core samples are both sampled to geology of between 0.15 and 1.2m intervals

Criteria	JORC Code explanation	Commentary
Orientation of data in relation to geological structure	 Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type. If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be assessed and reported if material. 	 No bias of sampling is believed to exist through the drilling orientation All drilling in this program is perpendicular to the interpreted orientation of the orebody.
Sample security	The measures taken to ensure sample security.	 The chain of custody is managed by Pantoro employees and contractors. Samples are stored on site and delivered in bulka bags to the lab in Kalgoorlie and when required transshipped to affiliated Perth Laboratory. Samples are tracked during shipping. Pre Pantoro operator sample security assumed to be consistent and adequate
Audits or reviews	The results of any audits or reviews of sampling techniques and data.	No audit or reviews of sampling techniques have been undertaken however the data is managed by company data scientist who has internal checks/protocols in place for all QA/QC.

SECTION 2: REPORTING OF EXPLORATION RESULTS

Criteria	JORC Code explanation	Commentary
Mineral tenement and land tenure status	 Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings. The security of the tenure held at the time of reporting along with any known impediments to obtaining a licence to operate in the area. 	

Criteria	JORC Code explanation	Commentary
Exploration done by other	Acknowledgment and appraisal of exploration by other parties.	Gold was discovered in the area 1894 and mining undertaken by small Syndicates.
parties		• In 1935 Western Mining established a presence in the region and operated the Mainfield and Northfield areas under the subsidiary company Central Norseman Gold Corporation Ltd. The Norseman asset was held within a company structure whereby both the listed CNGC held 49.52% and WMC held a controlling interest of 50.48%. They operated continuously until the sale to Croesus in October 2001 and operated until 2006. During the period of Croesus management the focus was on mining from the Harlequin and Bullen Declines accessing the St Pats, Bullen and Mararoa reefs. Open Pits were Scotia, HV1, Daisy, Gladstone and Golden Dragon with the focus predominantly on the high grade underground mines.
		 From 2006-2016 the mine was operated by various companies with exploration being far more limited than that seen in the previous years.
		• In 1990, a dedicated lake capable air core rig began testing on Lake Cowan beneath Tertiary sediment and Recent mud. This was the first successful drill rig of its type used on salt lakes in Australia with significant advances having been made since this time. These initial historic programs were drilled on regional traverses at a spacing of 2 km by 400 m, with a small number of targets tested at a closer spacing. The more focussed programs were designed to test features defined by interpretation of magnetic data at the confluence of interpreted favourable stratigraphy and structure. Sailfish was defined as part of this work along with the Harlequin and Cobbler deposits with wide spaced diamond drilling conducted at the time.
Geology	Deposit type, geological setting and style of mineralisation.	 The Norseman gold deposits are located within the southern portion of the Eastern Goldfields Province of Western Australia in the Norseman-Wiluna greenstone belt in the Norseman district. Deposits are predominantly associated with near north striking easterly dipping quartz vein within metamorphosed Archean mafic rocks of the Woolyeenyer Formation located above the Agnes Venture slates which occur at the base.
		 The principal units of the Norseman district, are greenstones which are west dipping and interpreted to be west facing. The sequence consists of the Penneshaw Formation comprising basalts and felsic volcanics on the eastern margin bounded by the Buldania granite batholith, the Noganyer Iron Formation, the Woolyeenyer formation comprising pillow basalts intruded by gabbros and the Mount Kirk Formation a mixed assemblage.

	Criteria	JORC Code explanation	Commentary
			• The mineralisation is hosted in quartz reefs in steeper shears and flatter linking sections, more recently significant production has been sourced from NNW striking reefs known as cross structures (Bullen). Whilst a number of vein types are categorized the gold mineralisation is predominantly located in the main north trending reefs which in the Mainfield strike for over a kilometre. The quartz/sulphide veins range from 0.5 metres up to 2 metres thick, these veins are zoned with higher grades occurring in the laminated veins on the margins and central bucky quartz which is white in colour. Bonanza grades are associated with native gold and tellurides with other accessory sulphide minerals being galena, sphalerite, chalcopyrite, pyrite and arsenopyrite.
			• The long running operations at Norseman have provided a good understanding on the controls of mineralisation as well as the structural setting of the deposits. The overall geology of the Norseman area is well understood with 3D Fractal Graphic mapping and detailed studies, adding to a good geological understanding to the area. The geometry of the main lodes at Norseman are well known and plunge of shoots predictable in areas, however large areas remain untested by drilling with the potential for new spurs and cross links high. Whilst the general geology of lodes is used to constrain all wireframes, predicting continuity of grade has proven to be difficult at the higher grades when mining and in some instances (containing about 7% of the ounces) subjective parameters have been applied.
U	Drill hole Information	A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes: ** easting and northing of the drill hole collar**	A table of drill hole data pertaining to this release is attached.
		» elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar	
		» dip and azimuth of the hole	
		» down hole length and interception depth	
		» hole length.	
		• If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.	

Criteria	eria JORC Code explanation		Cor	nmentary
Data aggregation methods	•	In reporting Exploration Results, weighting averaging techniques, maximum	•	Reported drill results are uncut
		and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated.	•	All relevant intervals to the reported mineralised intercept are length weighted to determine the average grade for the reported intercept.
	•	Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.	•	It should be noted that some of the reported intercepts have experienced significant core loss within the reported mineralized interval. As such the intervals of core loss are calculated on a weighted average basis with the intervals of core loss assigned 0.00g/t for the purpose of the reported interval. Where this is the
	•	The assumptions used for any reporting of metal equivalent values should be clearly stated.		case these intervals are clearly identified.
		clearly stated.	•	All significant intersections are reported with a lower cut off of 1 g/t Au including a maximum of 2m of internal dilution. Individual intervals below this cut off are reported where they are considered to be required in the context of the presentation of results
			•	No metal equivalents are reported.
Relationship between mineralisation widths and	•	These relationships are particularly important in the reporting of Exploration Results.	•	The diamond drilling of the is considered to be nominally perpendicular to the orebody as currently interpreted.
intercept lengths	•	If the geometry of the mineralisation with respect to the drill hole angle is known, its nature should be reported.	•	Downhole lengths are reported and true widths are not known at this time as the orebodies in the area have demonstrated variable orientations and widths.
	•	If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known').		
Diagrams	•	Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.	•	Given the preliminary nature of the reported mineralisation , appropriate diagrams are included in the report.
Balanced reporting	•	Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.	•	All holes available are reported are included in the tables
Other substantive exploration data	•	Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.	•	No other meaningful data to report.
Further work	•	The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling).	•	As already noted these drilling results are part of a ongoing evaluation drilling program to follow up on an historic prospect. The results are preliminary in nature
	•	Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.		and significant further work is required to establish if an economic deposit may eventuate. Larger diameter PQ diamond drilling has improved core recovery in the high grade zones. A larger extension program is now planned.

Exploration Targets, Exploration Results

The information in this report that relates to Exploration Targets and Exploration Results is based on information compiled by Mr Andrew Finch, a Competent Person who is a Member of the Australian Institute of Geoscientists. Mr Finch is a full time employee of the company. Mr Finch is eligible to participate in short and long term incentive plans of and holds shares and options in the Company. Mr Finch has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity being undertaken to qualify as a Competent Person as defined in the 2012 Edition of the 'Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves'. Mr Finch consents to the inclusion in the report of the matters based on his information in the form and context in which it appears.

Previous Sailfish Drilling Results

The information is extracted from the reports entitled 'Very High Grade Mineralisation Encountered on Lake Cowan' created on 21 July 2020 and available to view on Pantoro's website (www.pantoro.com.au) and the ASX (www.asx.com.au). The company confirms that it is not aware of any new information or data that materially affects the information included in the original market announcement. The company confirms that the form and context in which the Competent Person's findings are presented have not been materially modified from the original market announcement.

Norseman Gold Project Mineral Resources & Ore Reserves

The information is extracted from the report entitled 'DFS for the Norseman Gold Project' created on 12 October 2020 and is available to view on Pantoro's website (www.pantoro.com.au) and the ASX (www.asx.com.au). The company confirms that it is not aware of any new information or data that materially affects the information included in the original market announcement and, in the case of estimates of Mineral Resources or Ore Reserves, that all material assumptions and technical parameters underpinning the estimates in the relevant market announcement continue to apply and have not materially changed. The company confirms that the form and context in which the Competent Person's findings are presented have not been materially modified from the original market announcement.

Forward Looking Statements

Certain statements in this report relate to the future, including forward looking statements relating to Pantoro's financial position and strategy. These forward looking statements involve known and unknown risks, uncertainties, assumptions and other important factors that could cause the actual results, performance or achievements of Pantoro to be materially different from future results, performance or achievements expressed or implied by such statements. Actual events or results may differ materially from the events or results expressed or implied in any forward looking statement and deviations are both normal and to be expected. Other than required by law, neither Pantoro, their officers nor any other person gives any representation, assurance or guarantee that the occurrence of the events expressed or implied in any forward looking statements will actually occur. You are cautioned not to place undue reliance on those statements.